

Emerson & Cuming™

STYCAST® W 19 Very Low Viscosity, Epoxy Impregnant

Key Feature:	Benefit:
<ul style="list-style-type: none"> • Very low viscosity 	<ul style="list-style-type: none"> • Ease of use and dispensing
<ul style="list-style-type: none"> • Excellent impregnation 	<ul style="list-style-type: none"> • Complete encapsulation of tightly packed components and coils

Product Description:

STYCAST W 19 is an unfilled, 100% solids, epoxy impregnant that can be cured with a variety of catalysts. It can be used as a casting resin in applications where a small quantity (<25 grams) of material is needed.

Applications:

STYCAST W 19 is designed as an impregnant for tightly wrapped coils, small device potting, or as a surface coating applied by dip, brush, or spray.

Instructions For Use:

Thoroughly read the information concerning health and safety contained in this bulletin before using. Observe all precautionary statements that appear on the product label and/or contained in individual Material Safety Data Sheets (MSDS).

To ensure the long term performance of the potted or encapsulated electrical / electronic assembly, complete cleaning of components and substrates should be performed to remove contamination such as dust, moisture, salt, and

oils which can cause electrical failure, poor adhesion or corrosion in an embedded part.

Accurately weigh resin and hardener into a clean container in the recommended ratio. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.

Blend components by hand, using a kneading motion, for 2-3 minutes. Scrape the bottom and sides of the mixing container frequently to produce a uniform mixture. If possible, power mix for an additional 2-3 minutes. Avoid high mixing speeds which could entrap excessive amounts of air or cause overheating of the mixture resulting in reduced working life.

To eliminate moisture absorbed in coils, paper, and other insulation components, the part to be impregnated or potted should be preheated to 100-120°C. For coil molding, preheat the components and mold to 70-90°C prior to pouring.

Submerge components in reservoir containing the STYCAST W 19 and allow to stand until assembly is completely penetrated by the resin. Vacuum can be applied to ensure complete penetration in components containing tightly wound coils. Remove impregnated assembly from reservoir and allow to drain.

Resin "runoff" from impregnated components can be minimized during cure when using Catalyst 11 by allowing units to stand overnight at 25-35°C, then curing for 4 hours at 105°C.

Properties of Material As Supplied:

Property	Test Method	Unit	Value
Chemical Type			Epoxy
Appearance	Visual		Clear, red liquid
Density	ASTM-D-792	g/cm ³	1.20
Brookfield Viscosity	ASTM-D-2393	Pa.s cP	0.25 250

Choice of Curing Agents

Curing agent	Catalyst 9	Catalyst 11
Description	General purpose with good chemical resistance and physical strength.	Long pot life, excellent chemical resistance, good physical and chemical properties at elevated temperatures.
Type of cure	Room	Heat
Viscosity	Pa.s cP	0.080 to 0.105 80 to 105
		0.035 to 0.060 @ 65 °C 35 to 60 @ 65 °C

Properties of Material As Mixed:

Property	Test Method	Unit	Value	
			Catalyst 9	Catalyst 11
Mix Ratio - Catalyst per 100 parts of STYCAST W 19		By Weight By Volume	15 16.5	17.5 17.5
Working Life (100 g @ 25°C)	ERF 13-70		45 minutes	>4 hours
Density	ASTM-D-792	g/cm ³	1.09	1.11
Brookfield Viscosity	ASTM-D-2393	Pa.s cP	0.20 200	0.20 200

Cure Schedule:

Cure at any one of the recommended cure schedules. For optimum performance, follow the initial cure with a post cure of 2 - 4 hours at the highest expected use temperature. Alternate cure schedules may also be possible. Contact your Henkel Corporation Specialty Polymers Technical Representative for further information.

Temperature °C	Cure Time	
	Catalyst 9	Catalyst 11
25	16-24 hours	
45	4-6 hours	
65	1-2 hours	
80		8-16 hours
100		2-4 hours
120		30-60 minutes

Properties of Material After Application:

Property	Test Method	Unit	Value	
			Catalyst 9	Catalyst 11
Hardness	ASTM-D-2240	Shore D	78	78
Flexural Strength	ASTM-D-790	mPa psi		48 7,000
Water Absorption (7 days)	ASTM-D-570	%		0.2
Temperature Range of Use		°C	-40 to +130	-55 to +155
Dielectric Strength	ASTM-D-149	kV/mm V/mil	15.7 400	15.7 400
Dielectric Constant @ 1 MHz	ASTM-D-150	-		3.3
Dissipation Factor @ 1 MHz	ASTM-D-150	-		0.02
Volume Resistivity @ 25°C	ASTM-D-257	Ohm-cm	>10 ¹²	>10 ¹²

Storage and Handling:

The shelf life of STYCAST W 19 is 12 months at 25°C. For best results, store in original, tightly covered containers. Storage in cool, clean and dry areas is recommended. Usable shelf life may vary depending on method of application and storage conditions. Certain resins and hardeners are prone to crystallization. If crystallization does occur, warm the contents of the shipping container to 50-60°C until all crystals have dissolved. Be sure the shipping container is loosely covered during the warming stage to prevent any pressure build-up. Allow contents to cool to room temperature before continuing.

Health and Safety:

The STYCAST W 19, like most epoxy compounds, possesses the ability to cause skin and eye irritation upon contact. Certain individuals may also develop an allergic reaction after exposure (skin contact, inhalation of vapors, etc.) which may manifest itself in a number of ways including skin rashes and an itching sensation. Handling this product at elevated temperatures

may also generate vapors irritating to the respiratory system.

Good industrial hygiene and safety practices should be followed when handling this product. Proper eye protection and appropriate chemical resistant clothing should be worn to minimize direct contact. Consult the Material Safety Data Sheet (MSDS) for detailed recommendations on the use of engineering controls and personal protective equipment.

This information is only a brief summary of the available safety and health data. Thoroughly review the MSDS for more complete information before using this product.

Attention Specification Writers:

The values contained herein are considered typical properties only and are not intended to be used as specification limits. For assistance in preparing specifications, please contact Henkel Quality Assurance for further details..

Medical Implantable Disclaimer

"In the event this product is intended by you for use in implantation in the human body, you are hereby advised that Henkel Corporation has not performed clinical testing of these materials for implantation in the human body nor has Henkel Corporation sought, nor received, approval from the FDA for the use of these material in implantation in the human body. It is YOUR responsibility, as a manufacturer of any such device, to ensure that all materials and processes relating to the manufacture of any medical device fully comply with all applicable federal, state and local laws, rules, regulations and requirements as well as any such laws, rules, regulations, directives or other orders of any foreign country where such product is sold. If you have not undertaken the necessary investigations to ensure compliance you are advised NOT TO USE this product in the manufacture of any device which is to be implanted in the human body. No representative of ours has any authority to change the foregoing provisions."

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.**

The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel and/or its affiliates in Germany and elsewhere.

